



## Product Specifications

### SRW 7 Series Geogrid

SRW 7 Series Geogrid for soil and aggregate reinforcement, are manufactured of high tenacity, high molecular weight polyester yarns woven into a stable interlocking grid and then PVC coated to provide damage protection during installation. SRW Geogrid was developed for the reinforcement of steepened slopes, segmental retaining walls and for road base stabilization. It is biologically inert, resistant to most naturally encountered chemicals, alkalis, and acids, to ultra violet exposure and installation damage, and to long-term creep. Flexible for easy installation.

This product specification supersedes all prior specifications for the product described and is not applicable to any products shipped prior to November 1, 2009.

SRW Products assumes no liability for the completeness or accuracy of this information for the end use by the purchaser. This document is to assist, but should not be construed as engineering advice. SRW Products warrants that at the time of delivery the product furnished hereunder shall conform to the specification stated herein.

Grid Property	Direction	Unit	Test Method	Value
Weight (Avg)	-	oz/sq. yd.	ASTM D 5261	8.83
Aperture Size (Average)	MD/CMD	inch	measured w/ calipers	.75
Wide Width Tensile Strength	MD (at ultimate)	lbs/ft	ASTM D 4595	5000
Creep Limited Strength	MD	lbs/ft	ASTM D5262	3226
Ultimate Strain at Failure	MD	%	ASTM D 4595	15
Long Term Design Strength (LTDS)	MD	lb/ft RFCR=1.55, RFID=1.1, RFD=1.1	NCMA 97	2666

#### KEY:

MD=Machine Direction  
CMD=Cross Machine Direction

#### Partial reduction factors:

RFCR=for creep deformation  
RFID=for installation damage  
RFD=for durability

All values stated are Minimum Average Roll Values (unless otherwise stated). Based on a 95% confidence level.

SRW Geogrid is manufactured from polyester with a molecular weight (Mn) > 25,000 grams/mole and carboxyl end groups (CEG's) < 30 mmol/kg.

$$LTDS (MD) = \frac{T_{ultimate} (MD)}{RFCR \cdot RFID \cdot RFD} = \frac{5000}{1.55 \times 1.1 \times 1.1} = 2666 \text{ lb/ft}$$

**FHWA/AASHTO:** RFCR=1.55, RFID=1.05, RFD=1.15

**GRI:** RFCR=1.7, RFID=1.1, RFD=1.1

